



## Nickel Silver (% Max. unless shown as range or min.)

Family	Alloy	Cu%	Sn%	Pb%	Zn%	Fe%	Sb%	Ni%	S%	P%	Al%	Mn%	Si%	Bi%	Others
Nickel Silver	C97300	53.0-58.0 <sup>G</sup>	1.5-3.0	8.0-11.0	17.0-25.0	1.0	0.35	11.0-14.0	0.08	0.05	0.005	0.50	0.05	-	-
	C97600	63.0-66.0 <sup>N</sup>	3.5-4.5	3.5-5.0	3.0-9.0	1.0	0.25	19.5-21.0	0.08	0.05	0.005	1.0	0.05	-	-
	C97800	64.067.0 <sup>U</sup>	4.0-5.5	1.0-2.5	1.0-4.0	1.5	0.20	24.0-27.0	0.08	0.05	0.005	1.0	0.05	-	-

© The Federal Metal Company • 7250 Division Street • Bedford, Ohio 44146 • United States • Contact 800.736.6636 or visit us at: [www.federalmetal.com](http://www.federalmetal.com)

<sup>G</sup> Total named elements = 99.0% min.

<sup>H</sup> Total named elements = 99.5% min.

<sup>S</sup> Cr will be 0.05 max and Co 0.20 max.

<sup>T</sup> Ni > Fe