



Other Alloys (% Max. unless shown as range or min.)

Family	Alloy	Cu%	Sn%	Pb%	Zn%	Fe%	Sb%	Ni%	S%	P%	Al%	Mn%	Si%	Bi%	Others
Other Alloys	C94700	86.0-89.0 ^F	4.7-6.0	0.08R	1.3-2.5	0.20	0.10	4.5-6.0	0.05	0.05	0.005	0.20	0.005	–	–
	C94800	85.0-89.0 ^F	4.7-6.0	0.30-0.9	1.3-2.5	0.20	0.10	4.5-6.0	0.05	0.05	0.005	0.20	0.005	–	–
	C94900	79.0-81.0 ^M	4.3-6.0	4.0-5.7	4.3-6.0	0.25	0.25	4.5-6.0	0.08	0.05	0.005	0.10	0.005	–	–
	C99400	Remainer ^N	–	0.09	0.50-5.0	1.0-3.0	–	1.0-3.5 ^P	–	–	0.50-2.0	0.50	0.50-2.0	–	–
	C99500	Remainer ^N	–	0.09	0.50-2.0	3.0-5.0	–	3.5-5.5 ^P	–	–	0.50-2.0	0.50	0.50-2.0	–	–
	C99700	54.0min ^N	1.0	2.00	19.0-25.0	1.0	–	4.0-6.0 ^P	–	–	0.50-3.0	11.0-15.0	–	–	–
	C99750	55.0-61.0 ^N	–	0.50-2.5	17.0-23.0	1.0	–	5.0 ^P	–	–	0.25-3.0	17.0-23.-0	–	–	–

© The Federal Metal Company • 7250 Division Street • Bedford, Ohio 44146 • United States • Contact 800.736.6636 or visit us at: www.federalmetal.com

^F Cu + sum of named elements, 98.7%.

^G Total named elements = 99.0% min.

^M Cu + sum of named elements, 99.4%.

^N Cu + sum of named elements, 99.7%.

^U Cu + sum of named elements, 99.6%.